

**JANKA HARDNESS TABLE** Presented by:



CURUPAY	3850
PATAGONIAN ROSEWOOD	3840
AFRICAN PEARWOOD/MOABI	3680
BRAZILIAN WALNUT/IPE	3670
BRAZILIAN WALNUT/LAPACHO	3640
CUMARU/BRAZILIAN TEAK	3540
CARIBBEAN CHERRY	3100
SOUTHERN CHESTNUT	2670
STRAND WOVEN BAMBOO	2600
AFRICAN CEDAR/BOSSE	2600
BRAZILIAN CHERRY/JATOBA	2820
ACACIA	2400
BRAZILIAN MAPLE	2345
CARIBBEAN ROSEWOOD	2300
PYINKADO/IRONWOOD	2275
LYPTUS	2250
SANTOS MAHOGANY/CABREUVA	2200
ROSEWOOD/PRADOO	2170
TIGERWOOD	2160
SUCUPIRA	2140
AFRICAN ROSEWOOD/BUBINGA	1980
MERBAU	1925
AMENDOIM	1912
HICKORY/PECAN	1820
AFZELIA DOUSSIE	1770
AFRICAN CHERRY/PADAUK	1725
AFRICAN EBONY	1650
JEQUITIBA	1650
WENGE	1630
TIMBORANA	1570
AFORMOSIA	1560
SPANISH HICKORY	1570
AFRICAN MAHOGANY/SAPPELLE	1500
BRAZILIAN HICKORY/TAUARI	1480
HARD MAPLE	1450
CARIBBEAN WALNUT	1400
ROYAL MAHOGANY	1400
BAMBOO NATURAL	1380
AUSTRALIAN CYPRESS	1375
WHITE OAK	1360
ASH	1320
AMERICAN BEECH	1300
RED OAK	1290
AFRICAN TEAK/IROKO/KAMBALA	1260
YELLOW BIRCH	1260
HEART PINE	1225
BAMBOO CARBONIZED	1180
AMERICAN WALNUT	1010
TEAK	1000
AMERICAN CHERRY	950
SOUTHERN YELLOW PINE	870