


GUM, SYDNEY BLUE

Eucalyptus saligna



Appearance

COLOR: Wide range from pinks to burgundy reds; regrowth timber may be a pale straw color with pink highlights. Colors mute over time and darken to a medium brown-red.

Properties

HARDNESS (JANKA): 2023.

DIMENSIONAL STABILITY: Data not available.

Workability

NAILING: Pre-drilling and hand-nailing may be preferred.

SANDING: No known problems.

Suggested Sequence

First Cut: 50 at a 7-15 degree angle with the grain

Second Cut: 60 or 80 straight with the grain

Third Cut: 100

Hard Plate: 120

First Screen: 100

Second Screen: 120

FINISHING: No known finishing problems.

Origin

Australia.

Availability

Moderately available.